

# ARDROX<sup>®</sup> 2871A

## HIGHLY EFFECTIVE PAINT REMOVER

### 1 Description

Ardrox<sup>®</sup> 2871A is a peroxide-accelerated paint remover. It is designed to remove durable paint systems, such as epoxy and polyurethane, from aircraft and other surfaces.

It contains no halogenated solvents, and its low odor makes it an excellent choice in areas where personnel are working.

Ardrox<sup>®</sup> 2871A is neutral to slightly acidic and therefore safe on most materials.

#### Conformances

- ✓ Airbus                      ISO/SAE MA4872
- ✓ SAE                         ARP 1755 (partial)

Ask your Chemetall representative for a complete list of approvals

### 2 Physical and chemical properties

Property	Typical Value	Unit	Test Method
Appearance	Viscous, yellow emulsion	-	-
Odor	Characteristic	-	-
Density	1.02 - 1.06 @ 20°C 8.51 - 8.85 @ 68°F	g/ml lbs/gl	-
Flash point	>100°C	-	-

These are typical values only and do not constitute a specification.

### 3 Method of use

Ardrox<sup>®</sup> 2871A is ready for use as supplied.

#### 3.1 Surface preparation

Prior to the application of Ardrox<sup>®</sup> 2871A, any surface materials requiring masking should be accommodated. Consult your OEM or internal documentation for the appropriate masking procedures. Best results will be achieved at temperatures over 20 °C. The surface to be stripped should be cleaned, rinsed and dried prior to application of Ardrox<sup>®</sup> 2871A. Oil, dirt or other surface contaminants can interfere with the performance of Ardrox<sup>®</sup> 2871A.

For pre-cleaning we recommend the use of Ardrox<sup>®</sup> 6484A or Ardrox<sup>®</sup> 1900D.

#### 3.2 Application

Ardrox<sup>®</sup> 2871A is applied full strength by spraying with a piston-type pump and spray wand. Use with 2:1, 3:1, 5:1 or 10:1 pumps (5:1 and 10:1 preferred). Pouring is also possible.

Apply to a thickness of 2 to 3 times the coating thickness or until the paint is uniformly covered. Do not apply too much, otherwise sagging could occur. Personnel should always wear suitable protective clothing.

### 3.3 Paint removal

In general, Ardrox<sup>®</sup> 2871A should remain on the surface for 2 to 6 hours (depending on ambient temperatures, coating thickness, type of paint and other conditions). If it is necessary to bubble the paint, Ardrox<sup>®</sup> 2871A can be left on the surface for longer periods of time.

Note: Ardrox<sup>®</sup> 2871A is designed for a single-coat application and so does not require removal and reapplication in order to expedite removal.

### 3.4 Elimination

Removal of Ardrox<sup>®</sup> 2871A and paint can be achieved with the use of a squeegee, brush, rinsing with water, or equivalent method. Do not allow the softened paint to dry out as it may re-adhere to the substrate.

Spot reapply the stripper to remaining painted areas if necessary and repeat the removal method. Follow up with a final rinse or wipe using water or wash with Ardrox<sup>®</sup> 6484A or Ardrox<sup>®</sup> 1900D.

### 3.5 Pre-trial

Pour or spray Ardrox<sup>®</sup> 2871A on a vertical portion of the aircraft or panel. Record the coating thickness, time and temperature at application.

## 4 Effects on materials

Ardrox<sup>®</sup> 2871A is safe for aluminum, titanium, magnesium and most types of steel. Not to be used on windows or composites.

## 5 Shelf life, storage and disposal

Please refer to the corresponding Material Safety Data Sheets for details on shelf life, storage and disposal.

## 6 Labor and environmental protection

Before operating the process described it is important that this complete document, together with any relevant safety data sheets, be read and understood.

All local and national regulations on the transport, storage, use and waste treatment of chemicals in concentrated or diluted form and as working solutions must be obeyed.

## 7 General Information

Chemetall supplies a wide range of chemical products and associated equipment for cleaning, descaling, paint and carbon removal, metal working and protection and non-destructive testing. Sales Executives are available to advice on specific problems and applications.

The above details have been compiled to the best of our knowledge on the basis of tests and research work and with regard to the current state of our practical experience. This technical product information is non-binding. No liabilities or guarantees deriving from or in connection with this leaflet can be imputed to us. Statements relating to possible uses of the product do not constitute a guarantee that such uses are appropriate in a particular user's case or that such uses do not infringe the patents or proprietary rights of any third party. The reproduction of any or all of the information contained in this leaflet is expressly forbidden without Chemetall's prior written consent.

**Headquarters and Regional Head Office  
Europe, Middle East, Africa, South America**  
Chemetall GmbH  
Trakehner Straße 3  
60487 Frankfurt am Main, Germany  
Tel: +49 (0) 69 7165-0

**Regional Head Office  
North America**  
Chemetall US, Inc.  
675 Central Avenue  
New Providence, NJ 07974, USA  
Tel: +1-908-464-6900

**Regional Head Office  
Asia-Pacific**  
Chemetall Asia Pte Ltd.  
12 Loyang Crescent  
Singapore 508980  
Tel: +65 6885 7900