

LOCTITE EDAG 6017SS E&C

September 2014

PRODUCT DESCRIPTION

LOCTITE EDAG 6017SS E&C provides the following product characteristics:

Technology	Thermoplastic
Appearance	Black
Filler Type	Carbon
Cure	Heat cure
Operating Temperature-Maximum	100°C
Product Benefits	<ul style="list-style-type: none"> • Screen printable • Excellent screen residence time • Flexible low temperature drying cycles • Compatible with polyester film, paper and cardboard • Good adhesion to polyester film
Application	Conductive Ink
Typical Assembly Applications	Various resistive applications, Printed resistors, Heating elements, Sensing devices and Protection against electrostatic discharge (ESD)
Key Substrates	Polyester

LOCTITE EDAG 6017SS E&C screen printable ink is specifically designed for blending with EDAG PM 404 E&C to provide exceptional resistance in the production of low voltage circuitry on polyester film

TYPICAL PROPERTIES OF UNCURED MATERIAL

Solids Content by Weight, %	27
Viscosity, Brookfield, mPa·s (cP): Speed 20 rpm, @ 20°C	25,000
Density, Kg/cm ³	1,100
Shelf Life @ 5 to 30°C (from date of manufacture), year	1
Flash Point DIN 53213°C	78

TYPICAL SCREEN PRINTING PROCESS

Emulsion Thickness

Emulsion Thickness, µm	20 to 40
------------------------	----------

Recommended Squeegee

Polyurethane, durometer	70 to 75
-------------------------	----------

Recommended Screen Type

Monofilament polyester screen, threads/cm	61 to 90
Stainless steel screen, threads/cm	77 to 110

Printing Equipment Type

Manual
Semi-automatic
High speed reel-to-reel

TYPICAL CURING PERFORMANCE

Recommended Drying Conditions

5 to 10 minutes @ 120°C

Blends of LOCTITE EDAG 6017SS E&C and Electrodag PM-404 can be dried in conventional air circulated ovens.

Higher temperatures will shorten the drying time and will lead to more stable resistance values.

For high speed production, jet drying, infra-red drying and drying in high speed reel-to-reel equipment can be used.

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Coverage @ 10µm dry coating thickness, m ² /kg wet product	12
Adhesion, grade	5B

Electrical Properties

Sheet Resistivity

Blending ratios of LOCTITE EDAG 6017SS E&C and Electrodag PM-404, Dried 5 minutes @ 120°C, ohms/sq

Electrodag 6017SS (% by weight)	Electrodag PM-404 (% by weight)	@ 25µm dry coating thickness
100	0	35
90	10	50
80	20	70
70	30	105
60	40	170
50	50	290
40	60	675
30	70	2160
25	75	4500
20	80	35,000
10	90	> 1e9

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

DIRECTIONS FOR USE

1. LOCTITE EDAG 6017SS E&C is supplied ready for use and does not require dilution..
2. Stir LOCTITE EDAG 6017SS E&C prior to each use..
3. When mixing with Electrodag PM-404, use a stirrer..
4. If dilution is necessary, use 2-butoxy ethyl acetate (butylglycol acetate)..
5. If a gel structure forms after extended storage, the product may be warmed slightly in a water bath (not exceeding 50°C) and stirred. Very often, stirring is enough to obtain a proper viscosity again.

Clean-up

To clean screen and equipment, use Methyleneketone (MEK), MIBK, Acetone or similar solvents

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 5 to 30 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{N/mm}^2 \times 145 = \text{psi}$

$\text{MPa} = \text{N/mm}^2$

$\text{MPa} \times 145 = \text{psi}$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal

ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.3