

# Ardrox<sup>®</sup> 3968

## WATER-DISPLACING CORROSION INHIBITOR

### 1 Description

Ardrox<sup>®</sup> 3968 is a corrosion inhibiting, dewatering fluid which will excellently displace fresh or salt water from metal surfaces. It contains a volatile solvent and when this has evaporated, a very thin oil film remains which gives protection to the metal surface.

#### Approvals

✓ SAE	AMS 3065 (conformance)
✓ CFMI	CFM56
✓ GE	SPMC 70-80-02
✓ Messier-Dowty	PCS 2800
✓ Pratt & Whitney	SPMC 124-1
✓ Rolls Royce	OMat
✓ Turbomeca	TS 00800

Ask your Chemetall representative for a complete list of approvals

### 2 Physical and chemical properties

Property	Typical Value	Unit
Appearance	Straw brown liquid	-
Density	0.800 – 0.830 at 20 °C / 68 °F	g/ml
Flash point	Approx. 64 °C / 147 °F	-
Dry film weight	Approx. 2 g/m <sup>2</sup> (2 µm thickness)	-

These are typical values only and do not constitute a specification.

### 3 Typical use

In metal finishing operations Ardrox<sup>®</sup> 3968 provides an alternative to oven drying where the presence of the final thin oil film is not considered detrimental. As temporary corrosion prevention is provided, the method allows a delay between various processing systems without the danger of corrosion.

Ardrox<sup>®</sup> 3968 has extremely good spreading and penetrating properties and is, therefore, very suitable as an aid to freeing seized-up parts, particularly if these are wet. Due to its water displacing properties, Ardrox<sup>®</sup> 3968 will rapidly restore electrical equipment which has been subjected to flooding to an operative condition. Typical examples of this are electric motors, switchgear and automobile ignition systems.

The product can be used as a coating to neutralize the corrosive effects of fingerprints on metal, when applied before or immediately after handling.

### 4 Method of use

Ardrox<sup>®</sup> 3968 may be applied by any of the conventional methods such as brushing, dipping, spraying or swabbing.

Dipping tanks should be constructed with a sloping or conical bottom.

During use, water will accumulate at the bottom of the tank and should be periodically run off. Immersion times do not need to exceed five minutes and usually 2-3 minutes is adequate. Agitation of work in dipping processes should be avoided as this will tend to emulsify the displaced water.

## 5 Effects on materials

The product will not affect normal paint systems and is not corrosive to copper. It may cause some swelling of rubbers if they are continually immersed. However, if a thin film is applied, the effect will be minimal and will largely disappear as the solvent evaporates.

Mild steel is a suitable material for tank construction.

## 6 Shelf life, storage and disposal

Please refer to the corresponding Material Safety Data Sheets for details on shelf life, storage and disposal.

## 7 Labor and environmental protection

Before operating the process described it is important that this complete document, together with any relevant Safety Data Sheets, is read and understood. All local and national regulations on the transport, storage, use and waste treatment of chemicals in concentrated or diluted form and as working solutions must be obeyed.

## 8 General Information

Chemetall supplies a wide range of chemical products and associated equipment for cleaning, descaling, paint and carbon removal, metal working and protection and non-destructive testing. Sales Executives are available to advice on specific problems and applications.

The above details have been compiled to the best of our knowledge on the basis of tests and research work and with regard to the current state of our practical experience. This technical product information is non-binding. No liabilities or guarantees deriving from or in connection with this leaflet can be imputed to us. Statements relating to possible uses of the product do not constitute a guarantee that such uses are appropriate in a particular user's case or that such uses do not infringe the patents or proprietary rights of any third party. The reproduction of any or all of the information contained in this leaflet is expressly forbidden without Chemetall's prior written consent.

**Headquarters and Regional Head Office**  
**Europe, Middle East, Africa,**  
**South America**  
Chemetall GmbH  
Trakehner Straße 3  
60487 Frankfurt am Main  
Germany  
Tel: +49 (0) 69 7165-0  
surfacetreatment@chemetall.com

**Regional Head Office**  
**North America**  
Chemetall US, Inc.  
675 Central Avenue  
New Providence, NJ 07974  
USA  
Tel: +1-908-464-6900  
chemetallamericas@chemetall.com

**Regional Head Office**  
**Asia-Pacific**  
Chemetall Asia Pte Ltd.  
12 Loyang Crescent  
Singapur 508980  
Tel: +65 6885 7900  
cm.asia@chemetall.com

[www.Chemetall.com](http://www.Chemetall.com)